tesa AG 687-WCG/HCL 3163-Si-sti



Claim 1 (previously amended)

 An adhesive tape comprising a composite backing based on an oriented, coextruded, at least twolayer polypropylene film whose one side is provided with an adhesive composition wherein the cleavage strength of the composite backing is less than the bond strength of the adhesive.

Claim 2 (previously amended)

The adhesive tape according to claim 1, wherein the thickness of the backing is from 15 to 120 μm.

Claim 3 (previously amended)

 The adhesive tape according to claim 1, wherein the edges of the polypropylene film have a serrated cut.

Claim 4 (previously amended)

4. The adhesive tape according to claim 1, wherein the polypropylene film is corona treated or flame treated in order to improve the adhesion of the adhesive composition to the polypropylene film.

Claim 5 (previously amended)

The adhesive tape according to claim 1, wherein a primer layer is applied between the polypropylene film and the adhesive layer.

Claim 6 (previously amended)

6. The adhesive tape according to claim 1, wherein the side of the polypropylene film opposite the adhesive composition bears a coating.

Claim 7 (previously amended)

7. The adhesive tape according to claim 11, wherein the application rate of the release coating is from 0.1 to 3 g/m².

Claim 8 (previously amended)

The adhesive tape according to claim 1, wherein the adhesive composition is a solventborne

tesa AG 687-WCG/HCL 3163-SI-sti

adhesive composition based on styrene-isoprene-styrene copolymers.

Claim 9 (previously amended)

9. The adhesive tape according to claim 1, wherein the application rate of the adhesive composition is from 15 to 60 g/m².

Claim 10 (currently amended)

A method for detecting unauthorized broaching of a package, which comprises sealing said package with the adhesive tape of Claim 1, by virtue of the fact that on removal wherein when the adhesive tape is removed from the surface of a package the adhesive tape is irreversibly destroyed and clearly indicates an attempted broaching by tearing or splitting in the thickness direction.

Claim 11 (previously added)

11. The adhesive tape of Claim 6, wherein said coating is a release coating.

Claim 12 (previously added)

12. The adhesive tape of Claim 7, wherein said application rate is 0.2 to 1.5 gm².

Claim 13 (previously added)

13. The adhesive tape of Claim 9, wherein said application rate is from 20 to 30 gm².